

Messrs.

Date:

APPROVAL SHEET

Product Name : High Voltage Multilayer Ceramic Chip Capacitors

Part No. : MA Series

Description : Size 0805~2225, C0G(NPO) & X7R, 1~3KVdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園縣蘆竹鄉南山路二段 220-1 號 <http://www.pdc.com.tw>

Tel: 03-322-4471 ext: Fax: 03-322-5231 / 03-321-221

Contact: _____ Mobile: _____

SPECIFICATION FOR
HIGH VOLTAGE MULTILAYER CERAMIC CHIP CAPACITORS

Part No. : MA Series

Description : Size 0805~2225, C0G(NPO) & X7R, 1~3KVdc

<u>DRAWN BY</u>	<u>CHECKED BY</u>	<u>APPROVED BY</u>
蕭敏珍	蔡永承	巫宏俊

1. INTRODUCTION

MA Series green type capacitors are manufactured by using green materials without lead and cadmium. These capacitors feature series connection of multi-layer capacitor units in a MLCC to realize high voltage performance. Reliable performances are built-in through exact formulation of dielectric powders, preparation of conductive paste, advanced automatic manufacturing, and strict quality control to assure excellent control in dielectric thickness, electrode integrity, and electrode-to-termination continuity.

2. FEATURES

- a. Special interior design offers high voltage rating in a given case size.
- b. High reliability and stability.
- c. RoHS compliant
- d. HALOGEN compliant

3. APPLICATIONS


- a. DC to DC converter.
- b. High voltage coupling/DC blocking.
- c. Back-lighting inverters.
- d. LAN/WLAN interface.
- e. Modem.
- f. Power supplies.

4. HOW TO ORDER

<u>MA</u>	<u>1206</u>	<u>CG</u>	—	<u>120</u>	<u>J</u>	—	<u>202</u>	<u>PR</u>	<u>G</u>
<u>PDC Family</u>	<u>Size</u>	<u>Dielectric</u>		<u>Capacitance</u>	<u>Tolerance</u>		<u>Rated voltage</u>	<u>Packaging</u>	<u>Control Code</u>
	Inch (mm) 0805 (2012) 1206 (3216) 1210 (3225) 1808 (4520) 1812 (4532) 1825 (4563) 2220 (5750) 2225 (5763)	CG: C0G(NPO) XR: X7R		Two significant digits followed by no. of zeros. And R is in place of decimal point. eg.: R47=0.47pF 0R5=0.5pF 1R0=1.0pF 100=10x10 ⁰ =10pF	B =±0.1pF C =±0.25pF D =±0.5pF F =±1% G =±2% J =±5% K =±10% M =±20%		Two significant digits followed by no. of zeros. And R is in place of decimal point. 102 = 1000 VDC 202 = 2000 VDC 302 = 3000 VDC	ER: Tape and Reel, Embossed Tape PR: Tape and Reel, Paper Tape No Code: Bulk	G: RoHS compliant

5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	T(mm)	M _B min (mm)
0805 (2012)	2.00±0.20	1.25±0.20	1.45 max.	0.30
1206 (3216)	3.20±0.20	1.60±0.20	1.80 max.	0.30
1210 (3225)	3.20±0.40	2.50±0.30	2.80 max.	0.30
1808 (4520)	4.50±0.40	2.00±0.20	2.20 max.	0.26
1812 (4532)	4.50±0.40	3.20±0.30	2.80 max.	0.26
1825(4563)	4.50±0.40	6.30±0.40	2.80 max.	0.30
2220 (5750)	5.70±0.40	5.00±0.40	2.80 max.	0.30
2225 (5763)	5.70±0.40	6.30±0.40	2.80 max.	0.30



6. GENERAL ELECTRICAL DATA

Dielectric	C0G(NPO)		X7R
Size	0805,1206, 1210, 1808, 1812, 1825, 2220, 2225		0805,1206, 1210, 1808, 1812, 1825, 2220, 2225
Rated voltage (WVDC)	1KV, 2KV, 3KV		1KV, 1.5KV,2KV, 3KV
Capacitance range*	1.5pF ~ 12nF		100pF ~ 150nF
Capacitance tolerance	Cap. Rang	Tolerance Spec.	J (±5%), K (±10%), M (±20%)
	Cap≤5pF:	B (±0.1pF), C (±0.25pF)	
	5pF<Cap<10pF:	C (±0.25pF), D (±0.5pF)	
	10pF≤Cap:	F (±1%), G (±2%), J (±5%),K (±10%)	
Tan δ*	Cap. Rang	Q Spec.	≤2.5%
	Cap<30pF:	Q≥400+20C	
	Cap≥30pF:	Q≥1000	
Capacitance & Tan δ Test Condition	Measured at the condition of 30~70% related humidity.		Preconditioning for Class II MLCC: Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement.
	for 25°C at ambient temperature		
	Cap. Rang	Test Condition	
	Cap≤1000pF,	1.0±0.2Vrms, 1.0MHz±10%	Apply 1.0±0.2Vrms, 1.0kHz±10%, at 25°C ambient temperature.
	Cap>1000pF,	1.0±0.2Vrms, 1.0kHz±10%	
Insulation resistance	≥100GΩ or R•C≥ 500Ω•F whichever is smaller		≥10GΩ or R•C≥100Ω•F whichever is smaller
Operating temperature	-55 to +125°C		
Temperature coefficient	±30ppm / °C		±15%
Termination	Ag (or Cu)/Ni/Sn (lead-free termination)		

* Measured at the condition of 30~70% related humidity.

C0G(NPO): Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2Vrms, 1.0kHz±10% for Cap>1000pF, 25°C at ambient temperature

X7R: Apply 1.0±0.2Vrms, 1.0kHz±10%, at 25°C ambient temperature.

7. CAPACITANCE RANGE

DIELECTRIC		COG(NP0)											
SIZE	0805	1206		1210			1808			1812			
RATED VOLTAGE (VDC)	1000	1000	2000	1000	2000	3000	1000	2000	3000	1000	2000	3000	
Capacitance	0.5pF (0R5)												
	1.0pF (1R0)												
	1.5pF (1R5)												
	1.8pF (1R8)												
	2.2pF (2R2)												
	2.7pF (2R7)												
	3.3pF (3R3)												
	3.9pF (3R9)												
	4.7pF (4R7)												
	5.6pF (5R6)												
	6.8pF (6R8)												
	8.2pF (8R2)												
	10pF (100)												
	12pF (120)												
	15pF (150)												
	18pF (180)												
	22pF (220)												
	27pF (270)												
	33pF (330)												
	39pF (390)												
	47pF (470)												
	56pF (560)												
	68pF (680)												
	82pF (820)												
	100pF (101)												
	120pF (121)												
	150pF (151)												
	180pF (181)												
	220pF (221)												
	270pF (271)												
	330pF (331)												
	390pF (391)												
	470pF (471)												
	560pF (561)												
	680pF (681)												
	820pF (821)												
	1,000pF (102)												
	1,200pF (122)												
	1,500pF (152)												
	1,800pF (182)												
2,200pF (222)													
2,700pF (272)													
3,300pF (332)													
3,900pF (392)													
4,700pF (472)													
5,600pF (562)													
6,800pF (682)													
8,200pF (822)													
0.010μF (103)													

DIELECTRIC SIZE		C0G(NP0)								
		1825			2220			2225		
RATED VOLTAGE		1000	2000	3000	1000	2000	3000	1000	2000	3000
Capacitance	1.5pF (1R5)									
	1.8pF (1R8)									
	2.2pF (2R2)									
	2.7pF (2R7)									
	3.3pF (3R3)									
	3.9pF (3R9)									
	4.7pF (4R7)									
	5.6pF (5R6)									
	6.8pF (6R8)									
	8.2pF (8R2)									
	10pF (100)									
	12pF (120)									
	15pF (150)									
	18pF (180)									
	22pF (220)									
	27pF (270)									
	33pF (330)									
	39pF (390)									
	47pF (470)									
	56pF (560)									
	68pF (680)									
	82pF (820)									
	100pF (101)									
	120pF (121)									
	150pF (151)									
	180pF (181)									
	220pF (221)									
	270pF (271)									
	330pF (331)									
	390pF (391)									
	470pF (471)									
	560pF (561)									
	680pF (681)									
	820pF (821)									
	1,000pF (102)									
	1,200pF (122)									
1,500pF (152)										
1,800pF (182)										
2,200pF (222)										
2,700pF (272)										
3,300pF (332)										
3,900pF (392)										
4,700pF (472)										
5,600pF (562)										
6,800pF (682)										
8,200pF (822)										
0.010μF (103)										
0.012μF (123)										

DIELECTRIC		X7R											
SIZE	0805	1206			1210		1808				1812		
RATED VOLTAGE (VDC)	1000	1000	1500	2000	1000	2000	1000	1500	2000	3000	1000	2000	3000
Capacitance	100pF (101)												
	120pF (121)												
	150pF (151)												
	180pF (181)												
	220pF (221)												
	270pF (271)												
	330pF (331)												
	390pF (391)												
	470pF (471)												
	560pF (561)												
	680pF (681)												
	820pF (821)												
	1,000pF (102)												
	1,200pF (122)												
	1,500pF (152)												
	1,800pF (182)												
	2,200pF (222)												
	2,700pF (272)												
	3,300pF (332)												
	3,900pF (392)												
	4,700pF (472)												
	5,600pF (562)												
	6,800pF (682)												
	8,200pF (822)												
	0.010μF (103)												
	0.012μF (123)												
	0.015μF (153)												
	0.018μF (183)												
	0.022μF (223)												
	0.027μF (273)												
0.033μF (333)													
0.039μF (393)													
0.047μF (473)													
0.056μF (563)													

DIELECTRIC		X7R								
SIZE		1825			2220			2225		
RATED VOLTAGE(VDC)		1000	2000	3000	1000	2000	3000	1000	2000	3000
Capacitance	1,000pF (102)									
	1,200pF (122)									
	1,500pF (152)									
	1,800pF (182)									
	2,200pF (222)									
	2,700pF (272)									
	3,300pF (332)									
	3,900pF (392)									
	4,700pF (472)									
	5,600pF (562)									
	6,800pF (682)									
	8,200pF (822)									
	0.010μF (103)									
	0.012μF (123)									
	0.015μF (153)									
	0.018μF (183)									
	0.022μF (223)									
	0.027μF (273)									
	0.033μF (333)									
	0.039μF (393)									
	0.047μF (473)									
	0.056μF (563)									
	0.068μF (683)									
	0.082μF (823)									
0.10μF (104)										
0.12μF (124)										
0.15μF (154)										

8. PACKAGE DIMENSION AND QUANTITY

Size	Thickness (mm)	Paper tape		Plastic tape	
		7" reel	13" reel	7" reel	13" reel
0805 (2012)	0.80±0.10	4K	15k	-	-
	1.25±0.10	-	-	3k	10k
1206 (3216)	0.80±0.10	4k	15k	-	-
	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
1210 (3225)	1.60±0.20	-	-	2k	-
	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	-
	2.00±0.20	-	-	1k	-
1808 (4520)	2.50±0.30	-	-	1k	-
	1.25±0.10	-	-	2k	-
	1.40±0.15	-	-	2k	-
	1.60±0.20	-	-	2k	-
1812 (4532)	2.00±0.20	-	-	1k	-
	1.25±0.10	-	-	1k	-
	1.60±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	3k
1825 (4563)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2220 (5750)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
2225 (5763)	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-

Unit: pieces




Fig. 4 The dimension of reel

Size	0805, 1206, 1210, 1812			1808, 1812, 1825, 2220, 2225
	7"	10"	13"	7"
C	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2	13.0+0.5/-0.2
W _i	8.4+1.5/-0	8.4+1.5/-0	8.4+1.5/-0	12.4+2.0/-0
A	178.0±0.10	250.0±1.0	330.0±1.0	178.0±0.10
N	60.5±1.0	100.0±1.0	100±1.0	60.5±1.0

8-1. CARDBOARD TAPE DIMESIONS




Fig. 2 The dimension of paper tape

8-2. EMBOSSED TAPE DIMENSIONS




Fig. 3 The dimension of plastic tape

Size	0805		1206			1210		1808	
Chip Thickness	0.80±0.10	1.25±0.10	0.80±0.10	0.95±0.10 1.25±0.10	1.60±0.20 1.60+0.3/-0.1	0.95±0.10 1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30	1.25±0.10 1.40±0.15 1.60±0.20	2.00±0.20
A ₀	1.50±0.10	<1.65	2.00±0.10	<2.00	<2.00	<3.05	<3.10	<2.50	<2.50
B ₀	2.30±0.10	<2.40	3.50±0.10	<3.60	<3.70	<3.80	<4.00	<5.30	<5.30
T	0.95±0.05	0.23±0.05	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.25±0.05	0.25±0.05
K ₀	-	<2.50	-	<2.50	<2.50	<2.50	<3.50	<2.50	<2.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	12.0±0.20	12.0±0.20
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.100	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.00±0.20	40.00±0.20	40.0±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.0±0.20	40.0±0.20	40.0±0.20
P ₁	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.55±0.05	1.50±0.10/ -0	1.50±0.05	1.50±0.10/-0	1.50±0.10/-0	1.50±0.10/-0	1.50±0.10/-0	1.50±0.10/-0	1.50±0.10/-0
D ₁	-	1.00±0.10	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.50±0.10	1.50±0.10
E	1.75±0.05	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	5.50±0.05	5.50±0.05

Size	1812		1825		2220		2225	
Chip Thickness	1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30	2.00±0.20	2.50±0.30	1.40±0.15 1.60±0.20 2.00±0.20	2.50±0.30	2.00±0.20	2.50±0.30
A ₀	<3.90	<3.90	<6.80	<6.80	<5.80	<5.80	<6.80	<6.80
B ₀	<5.30	<5.30	<5.30	<5.30	<6.50	<6.50	<6.50	<6.50
T	0.25±0.05	0.25±0.05	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10
K ₀	<2.50	<3.0	<2.50	<3.10	<2.50	<3.10	<2.50	<3.10
W	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20	12.0±0.20
P ₀	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP ₀	40.0±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.0±0.20	40.0±0.20	40.0±0.20	40.0±0.20
P ₁	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P ₂	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D ₀	1.50+0.10/-0.00	1.50+0.10/-0.00	1.50+0.10/-0.00	1.50+0.10/-0.00	1.50+0.10/-0.00	1.50+0.10/-0.00	1.50+0.10/-0	1.50+0.10/-0
D ₁	1.50±0.10	1.50+/-0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75+/-0.1	1.75±0.1	1.75±0.10	1.75±0.1	1.75±0.10	1.75±0.10	1.75±0.10
F	5.50±0.05	5.50+/-0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05

9. APPLICATION NOTES

STORAGE

To prevent the damage of solderability of terminations, the following storage conditions are recommended:

Indoors under 5 ~ 40°C and 20% ~ 70% RH.

No harmful gases containing sulfuric acid, ammonia, hydrogen sulfide or chlorine.

Packaging should not be opened until the capacitors are required for use. If opened, the pack should be re-sealed as soon as is practicable. Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesion performance. The capacitors should be used within 6 months and checked the solderability before use.

HANDLING

Chip capacitors are dense, hard, brittle, and abrasive materials. They are liable to suffer mechanical damage, in the form of cracks or chips. Chip Capacitors should be handled with care to avoid contamination or damage. To use vacuum or plastic tweezers to pick up or plastic tweezers is recommended for manual placement. Tape and reeled packages are suitable for automatic pick and placement machine.

PREHEAT

In order to minimize the risk of thermal shock during soldering, a carefully controlled preheat is required. The rate of preheat should not exceed 4°C per second and the final preheat temperature should be within 100°C of the soldering temperature for small chips such as 0805,1206, within 50°C of the soldering temperature for bigger chips such as 1210, 1808, 1812, 1825, 2220 and 2225, etc.


SOLDERING

Use mildly activated rosin RA and RMA fluxes do not use activated flux. The amount of solder in each solder joint should be controlled to prevent the damage of chip capacitors caused by the stress between solder, chips, and substrate.

Hand soldering with temperature-controlled iron not exceeding 30 watts and diameter of tip less than 1.2 mm is recommended, tip of iron should not contact the ceramic body directly, and the temperature of iron should be set to not more than 260°C.

For bigger chips such as 1210, 1808, 1812, 2220 and 2225, etc. wave soldering and hand soldering are no recommended.

Recommended soldering profiles as following:



Soldering	Solder Temp.(T)	Soldering Time (t)
Reflow	235 – 260 °C	< 15 sec.
Wave	230 – 260 °C	< 5 sec.

Chip Size	ΔT
0805,1206	100 °C
1210, 1808, 1812, 1825, 2220, 2225	50 °C

COOLING

After soldering, cool the chips and the substrate gradually to room temperature. Natural cooling in air is recommended to minimize stress in the solder joint. A cooling rate not exceeding 4°C per second should be used when forced cooling is necessary.



CLEANING

All flux residues must be removed by using suitable electronic-grade vapor-cleaning solvents to eliminate contamination that could cause electrolytic surface corrosion. Good results can be obtained by using ultrasonic cleaning of the solvent. The choice of the proper system is depends upon many factors such as component mix, flux, and solder paste and assembly method. The ability of the cleaning system to remove flux residues and contamination from under the chips is very important.

10.RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Condition	Requirements																										
1.	Visual and Mechanical	---	<ul style="list-style-type: none"> * No remarkable defect. * Dimensions to conform to individual specification sheet. 																										
2.	Capacitance	Class I: (C0G)	* Shall not exceed the limits given in the detailed spec.																										
3.	Q/ D.F. (Dissipation Factor)	Cap \leq 1000pF, 1.0 \pm 0.2Vrms, 1MHz \pm 10% Cap $>$ 1000pF, 1.0 \pm 0.2Vrms, 1KHz \pm 10% Class II: (X7R) 1.0 \pm 0.2Vrms, 1KHz \pm 10%	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Rated vol.(V)</th> <th>Q/D.F.</th> <th>Remark</th> </tr> </thead> <tbody> <tr> <td rowspan="2">Class I(NPO)</td> <td rowspan="2">≥ 50</td> <td>Q\geq1000</td> <td>Cap\geq30pF</td> </tr> <tr> <td>Q\geq400+20C</td> <td>Cap$<$30pF</td> </tr> <tr> <td>Class II(X7R)</td> <td>≥ 50</td> <td>D.F. $<$ 2.5%</td> <td></td> </tr> </tbody> </table>	Dielectric	Rated vol.(V)	Q/D.F.	Remark	Class I(NPO)	≥ 50	Q \geq 1000	Cap \geq 30pF	Q \geq 400+20C	Cap $<$ 30pF	Class II(X7R)	≥ 50	D.F. $<$ 2.5%													
Dielectric	Rated vol.(V)	Q/D.F.	Remark																										
Class I(NPO)	≥ 50	Q \geq 1000	Cap \geq 30pF																										
		Q \geq 400+20C	Cap $<$ 30pF																										
Class II(X7R)	≥ 50	D.F. $<$ 2.5%																											
4.	Temperature Coefficient	With no electrical load. <table border="1"> <thead> <tr> <th>T.C.</th> <th>Operating Temp</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>-55~125°C at 25°C</td> </tr> <tr> <td>X7R</td> <td>-55~125°C at 25°C</td> </tr> </tbody> </table>	T.C.	Operating Temp	C0G	-55~125°C at 25°C	X7R	-55~125°C at 25°C	<table border="1"> <thead> <tr> <th>T.C.</th> <th>Capacitance Change</th> </tr> </thead> <tbody> <tr> <td>C0G</td> <td>Within \pm30ppm/°C</td> </tr> <tr> <td>X7R</td> <td>Within \pm15%</td> </tr> </tbody> </table>	T.C.	Capacitance Change	C0G	Within \pm 30ppm/°C	X7R	Within \pm 15%														
T.C.	Operating Temp																												
C0G	-55~125°C at 25°C																												
X7R	-55~125°C at 25°C																												
T.C.	Capacitance Change																												
C0G	Within \pm 30ppm/°C																												
X7R	Within \pm 15%																												
5.	Insulation Resistance	To apply voltage at 500VDC for 60 sec.	<table border="1"> <thead> <tr> <th>Dielectric</th> <th>Requirements</th> </tr> </thead> <tbody> <tr> <td>Class I(NPO)</td> <td>\geq100GΩ or Rx$C \geq$ 500Ω-F whichever is smaller</td> </tr> <tr> <td>Class II(X7R)</td> <td>\geq10GΩ or Rx$C \geq$ 100Ω-F whichever is smaller.</td> </tr> </tbody> </table>	Dielectric	Requirements	Class I(NPO)	\geq 100G Ω or Rx $C \geq$ 500 Ω -F whichever is smaller	Class II(X7R)	\geq 10G Ω or Rx $C \geq$ 100 Ω -F whichever is smaller.																				
Dielectric	Requirements																												
Class I(NPO)	\geq 100G Ω or Rx $C \geq$ 500 Ω -F whichever is smaller																												
Class II(X7R)	\geq 10G Ω or Rx $C \geq$ 100 Ω -F whichever is smaller.																												
6.	Dielectric Strength	<table border="1"> <thead> <tr> <th>Rated vol.(V)</th> <th>Condition</th> </tr> </thead> <tbody> <tr> <td>1000 \leq V \leq 3000</td> <td>1.2 times of U_R</td> </tr> <tr> <td>4000 \leq V \leq 5000</td> <td>1.1 times of U_R</td> </tr> <tr> <td>$>$ 5000</td> <td>1.0 times of U_R</td> </tr> </tbody> </table> Duration: 1 to 5 sec.	Rated vol.(V)	Condition	1000 \leq V \leq 3000	1.2 times of U _R	4000 \leq V \leq 5000	1.1 times of U _R	$>$ 5000	1.0 times of U _R	<ul style="list-style-type: none"> * No evidence of damage or flashover during test. 																		
Rated vol.(V)	Condition																												
1000 \leq V \leq 3000	1.2 times of U _R																												
4000 \leq V \leq 5000	1.1 times of U _R																												
$>$ 5000	1.0 times of U _R																												
7.	Solderability	<ul style="list-style-type: none"> * Solder temperature: 235\pm5°C for (1206~1210) * Solder temperature: 245\pm5°C for (1808~2225) * Dipping time: 2\pm0.5 sec. 	75% min. coverage of all metalized area.																										
8.	Resistance to Soldering Heat	<ul style="list-style-type: none"> * Solder temperature: 260\pm5°C * Dipping time: 10\pm1 sec * Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48\pm4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24\pm2 hrs (Class I) or 48\pm4 hrs (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R</th> <th>Cap Change</th> <th>Q/D.F</th> </tr> </thead> <tbody> <tr> <td>Class I(NPO)</td> <td>$\geq 1G\Omega$</td> <td>Within \pm2.5% or \pm0.25pF whichever is larger.</td> <td>$\leq 1.0 \times$ Initial requirement</td> </tr> <tr> <td>Class II(X7R)</td> <td>$\geq 1G\Omega$</td> <td>within \pm7.5%</td> <td></td> </tr> </tbody> </table> <ul style="list-style-type: none"> * 25% max. leaching on each edge. 	Dielectric	I.R	Cap Change	Q/D.F	Class I(NPO)	$\geq 1G\Omega$	Within \pm 2.5% or \pm 0.25pF whichever is larger.	$\leq 1.0 \times$ Initial requirement	Class II(X7R)	$\geq 1G\Omega$	within \pm 7.5%															
Dielectric	I.R	Cap Change	Q/D.F																										
Class I(NPO)	$\geq 1G\Omega$	Within \pm 2.5% or \pm 0.25pF whichever is larger.	$\leq 1.0 \times$ Initial requirement																										
Class II(X7R)	$\geq 1G\Omega$	within \pm 7.5%																											
9.	Temperature Cycle	Conduct the five cycles according to the temperatures and time. <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30\pm3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30\pm3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 48\pm4 hrs at room temp. * Measurement to be made after keeping at room temp. for 24\pm2 hrs (Class I) or 48\pm4 hrs (Class II). 	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30 \pm 3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30 \pm 3	4	Room temp.	2~3	<ul style="list-style-type: none"> * No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R</th> <th>Cap Change</th> <th>Q/D.F</th> </tr> </thead> <tbody> <tr> <td>Class I(NPO)</td> <td rowspan="2">0.25 \times initial requirements.</td> <td>Within \pm2.5% or \pm0.25pF whichever is larger.</td> <td>$\leq 1.0(Q) \times$ Initial requirement</td> </tr> <tr> <td>Class II(X7R)</td> <td>within \pm7.5%</td> <td>$\leq 1.5(D.F.) \times$ Initial requirement</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * I.R.\geq 0.25 \times initial requirements. 	Dielectric	I.R	Cap Change	Q/D.F	Class I(NPO)	0.25 \times initial requirements.	Within \pm 2.5% or \pm 0.25pF whichever is larger.	$\leq 1.0(Q) \times$ Initial requirement	Class II(X7R)	within \pm 7.5%	$\leq 1.5(D.F.) \times$ Initial requirement
Step	Temp. (°C)	Time (min.)																											
1	Min. operating temp. +0/-3	30 \pm 3																											
2	Room temp.	2~3																											
3	Max. operating temp. +3/-0	30 \pm 3																											
4	Room temp.	2~3																											
Dielectric	I.R	Cap Change	Q/D.F																										
Class I(NPO)	0.25 \times initial requirements.	Within \pm 2.5% or \pm 0.25pF whichever is larger.	$\leq 1.0(Q) \times$ Initial requirement																										
Class II(X7R)		within \pm 7.5%	$\leq 1.5(D.F.) \times$ Initial requirement																										
10.	Humidity (Damp Heat) Steady State	<ul style="list-style-type: none"> * Test temp.: 40\pm2°C * Humidity: 90~95% RH * Test time: 500+24/-0hrs. * Measurement to be made after keeping at room temp. for 24\pm2 hrs (Class I) or 48\pm4 hrs (Class II). 	<ul style="list-style-type: none"> * No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R</th> <th>Cap Change</th> <th>Q/D.F</th> </tr> </thead> <tbody> <tr> <td rowspan="2">Class I(NPO)</td> <td rowspan="2">$\geq 1G\Omega$ or Rx$C \geq$ 25Ω-F whichever is smaller.</td> <td rowspan="2">within \pm3.0% or \pm2pF whichever is larger</td> <td>Cap \geq30pF</td> <td>Q\geq350;</td> </tr> <tr> <td>10pF \leq Cap $<$ 30pF</td> <td>Q\geq275+2.5C</td> </tr> <tr> <td>Class II(X7R)</td> <td></td> <td>within \pm15%</td> <td>Cap $<$ 10pF</td> <td>Q\geq200+10C</td> </tr> <tr> <td colspan="3"></td> <td colspan="2">D.F. $\leq 2 \times$ Initial requirement</td> </tr> </tbody> </table>	Dielectric	I.R	Cap Change	Q/D.F	Class I(NPO)	$\geq 1G\Omega$ or Rx $C \geq$ 25 Ω -F whichever is smaller.	within \pm 3.0% or \pm 2pF whichever is larger	Cap \geq 30pF	Q \geq 350;	10pF \leq Cap $<$ 30pF	Q \geq 275+2.5C	Class II(X7R)		within \pm 15%	Cap $<$ 10pF	Q \geq 200+10C				D.F. $\leq 2 \times$ Initial requirement						
Dielectric	I.R	Cap Change	Q/D.F																										
Class I(NPO)	$\geq 1G\Omega$ or Rx $C \geq$ 25 Ω -F whichever is smaller.	within \pm 3.0% or \pm 2pF whichever is larger	Cap \geq 30pF	Q \geq 350;																									
			10pF \leq Cap $<$ 30pF	Q \geq 275+2.5C																									
Class II(X7R)		within \pm 15%	Cap $<$ 10pF	Q \geq 200+10C																									
			D.F. $\leq 2 \times$ Initial requirement																										
11.	High Temperature Load (Endurance)	<ul style="list-style-type: none"> * Test temp.: 125\pm3°C <table border="1"> <thead> <tr> <th>Rated vol.(V)</th> <th>Apply Voltage</th> </tr> </thead> <tbody> <tr> <td>1000 \leq V \leq 5000</td> <td>1.1 times of U_R</td> </tr> <tr> <td>$>$ 5000</td> <td>1.0 times of U_R</td> </tr> </tbody> </table> <ul style="list-style-type: none"> * Test time: 1000+24/-0 hrs. * Measurement to be made after keeping at room temp. for 24\pm2 hrs (Class I) or 48\pm4 hrs (Class II). 	Rated vol.(V)	Apply Voltage	1000 \leq V \leq 5000	1.1 times of U _R	$>$ 5000	1.0 times of U _R	<ul style="list-style-type: none"> * No remarkable damage. <table border="1"> <thead> <tr> <th>Dielectric</th> <th>I.R</th> <th>Cap Change</th> <th>Q/D.F</th> </tr> </thead> <tbody> <tr> <td>Class I(NPO)</td> <td rowspan="2">$\geq 1G\Omega$ or Rx$C \geq$ 50Ω-F whichever is smaller.</td> <td>within \pm3.0% or \pm2pF whichever is larger</td> <td rowspan="2">D.F. $\leq 2 \times$ Initial requirement</td> </tr> <tr> <td>Class II(X7R)</td> <td>within \pm12.5%</td> </tr> </tbody> </table>	Dielectric	I.R	Cap Change	Q/D.F	Class I(NPO)	$\geq 1G\Omega$ or Rx $C \geq$ 50 Ω -F whichever is smaller.	within \pm 3.0% or \pm 2pF whichever is larger	D.F. $\leq 2 \times$ Initial requirement	Class II(X7R)	within \pm 12.5%										
Rated vol.(V)	Apply Voltage																												
1000 \leq V \leq 5000	1.1 times of U _R																												
$>$ 5000	1.0 times of U _R																												
Dielectric	I.R	Cap Change	Q/D.F																										
Class I(NPO)	$\geq 1G\Omega$ or Rx $C \geq$ 50 Ω -F whichever is smaller.	within \pm 3.0% or \pm 2pF whichever is larger	D.F. $\leq 2 \times$ Initial requirement																										
Class II(X7R)		within \pm 12.5%																											

10.RELIABILITY TEST CONDITIONS AND REQUIREMENTS(Cont.)

No.	Item	Test Condition	Requirements						
12.	Resistance to Flexure of Substrate	<p>* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm.</p> 	<p>* No remarkable damage.</p> <table border="1"> <thead> <tr> <th>Dielectric</th> <th>Cap Change</th> </tr> </thead> <tbody> <tr> <td>Class I(NPO)</td> <td>within $\pm 3.0\%$ or $\pm 2\text{pF}$ whichever is larger</td> </tr> <tr> <td>Class II(X7R)</td> <td>within $\pm 12.5\%$</td> </tr> </tbody> </table> <p>(This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)</p>	Dielectric	Cap Change	Class I(NPO)	within $\pm 3.0\%$ or $\pm 2\text{pF}$ whichever is larger	Class II(X7R)	within $\pm 12.5\%$
Dielectric	Cap Change								
Class I(NPO)	within $\pm 3.0\%$ or $\pm 2\text{pF}$ whichever is larger								
Class II(X7R)	within $\pm 12.5\%$								
13.	Adhesive Strength of Termination	<p>* Capacitors mounted on a substrate. A force of 10N applied perpendicular to the place of substrate and parallel the line joining the center of terminations for 10 ± 1 sec.</p> 	<p>* No remarkable damage or removal of the terminations.</p>						